(54) Title: OPTICAL FIBER

(57) Abstract: In an optical fiber 1 having a core region 3 and a cladding region 5 which surrounds the core region 3. wherein a plurality of regions made of sub mediums 2 having refractive index different from that of the main medium 4 constituting the cladding region 5 are spaced apart in cross section of the cladding region 5 and the mean refractive index of the core region 3 is lower than that of the cladding region 5. the sub-medium regions 2 are regularly arranged in the radial direction of the optical fiber 1 such that the light having given wavelength. propagation coefficient and electric field distribution propagates along the fiber axis and has not less than 50 % of a total propagating power in the core region 3. and this arrangement does not have translational symmetry in cross section.

WO 01/88578 A2

DESCRIPTION

OPTICAL FIBER

Technical Field

5   The present invention relates to an optical fiber suitable as an optical transmission path, a dispersion compensator, an optical filter, an optical power equalizer and an optical amplifier.

Background Art

Conventionally, optical fibers composed of
10   alternately arranged annular layers of high and low refractive indices have been known and disclosed in J. Marcou, et al., "Monomode photonic band gap fibers for dispersion shifting towards short wavelengths" ECOC'99, I-pp.24-25 (hereinafter called D1) and Y. Fink, et al., "Guiding optical
15   light in air using an all-dielectric structure" Journal of Lightwave Technology, vol.17, No.11, November, 1999 pp, 2039-2041 (hereinafter called D2).

In these optical fibers, light is confined in the center region, which is called the core region, surrounded by
20   annular layers, which is called the cladding region. The refractive index of the core region is lower than the refractive indices of the annular layers in the cladding region. Accordingly, the confinement of light in the core is not based on total internal reflection but on Bragg
25   reflection due to the regularity in the radial profile of refractive index. That is, a diverging cylindrical wave

centered at the fiber axis is strongly coupled to a converging cylindrical wave centered at the fiber axis because of the regularity in the radial profile of refractive index in the cladding region. As a result, the diverging cylindrical wave is reflected by the annular layers in the cladding, and is confined in the core.

The thicknesses of the annular layers in the cladding are not necessarily uniform. In D1, the refractive index distribution is designed to have the periodicity based on the Bessel functions, while in the D2, the thicknesses of the layers are determined in accordance with the zero points of the Bessel functions.

Further, in R.F. Cregan, et al "Single-Mode photonic band gap guidance of light in air", Science, vol.285, pp.1537-1539 (September, 1999)(hereinafter called D3), an optical fiber having a cross-sectional structure in which a defect is introduced in a refractive index periodic structure having a two-dimensional translational symmetry is disclosed. In the cross section of this optical fiber, small regions (cells) having given refractive index distribution are regularly arranged, and some of the cells are replaced with cells having different refractive index distribution, resulting in breaking of the translational symmetry of the cross-sectional refractive index distribution. Those symmetry-breaking cells are called defects.

The two-dimensional periodic structure of the refractive index, if properly designed, reflects light belonging to a given wavelength band regardless of angle of incidence. Such a wavelength band is called a full PBG (full Photonic Band Gap). The light having the wavelength within the PBG is confined in the defect in the periodic structure. The periodic structure and the defect extend along the fiber axis and hence, the light propagates along the fiber axis.

Further, U.S. Patent 5,802,236 discloses an optical fiber which includes a core and a cladding, wherein the effective refractive index of the core is higher than the effective refractive index of the cladding and the cladding has cladding feature structures which are arranged non-periodically. In such an optical structure, since the effective refractive index of the core is higher than the effective refractive index of the cladding, the light is confined in the core by total internal reflection. Here, assuming that a non-uniform region having spatially varying refractive index can be replaced with a homogeneous medium with maintaining the same optical characteristics, the effective refractive index is defined as the refractive index of such a homogeneous medium.

It is also conventionally known that Bragg reflection mirror can be formed by regularly laminating planar thin films consisting of media having different refractive

indices, and that a high reflection efficiency is achieved by meeting the quarter wavelength condition where the optical thicknesses of the thin films are equal to a quarter wavelength.

Disclosure of the Invention

5

However, in the optical fiber disclosed in D1, the refractive index difference between neighboring two annular layers is small (relative refractive index difference being 0.5 %) because it is formed by doping Ge into silica glass. Accordingly, the reflection efficiency of the annular layers

10

in the cladding becomes small, and hence optical confinement to the core becomes weak. As a result, the optical power leaks to the outside of the fiber so that the transmission loss, particularly the transmission loss due to the bending

15

of the fiber, increases.

On the other hand, in the optical fiber described in D2, the cladding region is composed of tellurium (refractive index being 4.6) and polystyrene (refractive index being 1.59). Due to the large difference in refractive index

20

between the media, a high reflection efficiency can be obtained. However, the fabrication of this optical fiber is difficult for the following reason. According to the fabrication method disclosed in D2, this optical fiber is obtained by alternately depositing a tellurium film having

25

a thickness of approximately 0.8 μm and a polystyrene film having a thickness of approximately 1.6 μm on an outer

4

periphery of a glass tube of a diameter of 1.92 mm. However, it is difficult to fabricate a long fiber uniformly by this method. This is because if the optical fiber is wound in a coil while the films are deposited on it, it is difficult

5   to deposit the films with uniform thickness. On the other hand, if the fiber is not wound in a coil shape, it is difficult to fabricate a long fiber because the length is limited by the size of the depositing facility. For example, the fiber length which is reported in the above-mentioned literature

10   is as short as 10 cm. Further, since the films are deposited on a cylindrical surface, the control of the film thickness is difficult compared with the conventional thin film forming where the films are deposited on a planar surface. This also makes it difficult to fabricate a fiber which is uniform

15   along its axis.

Further, in the optical fiber described in D3, the size of the defect is limited to integer times of the size of the cells of the periodic structure in the cross-sectional refractive index distribution. Accordingly, the size of

20   the core is also limited to integer times of the size of the cells. The diameter of the core affects the number of guided modes and the degree of the optical confinement of the guided modes. Accordingly, the limited range of selection of the core diameter results in the limited range

25   of achievable optical characteristics of the optical fiber. Particularly, it becomes difficult to deliberately control

5

the wavelength range for single-mode operation and the tolerance to bending.

The present invention has been made in view of the above and it is an object of the present invention to provide an optical fiber based on confinement by Bragg reflection which exhibits strong optical confinement to the core, facilitates the fabrication of a long fiber, and realizes a high freedom in selection of the core diameter.

To achieve such an object, the optical fiber according to the present invention is the optical fiber consisting of a core region and a cladding region which surrounds the core region and has a plurality of regions spaced apart in cross section and made of sub mediums, whose refractive indices differ from that of a main medium constituting the cladding region, wherein the core region has lower mean refractive index than that of the cladding region, and wherein the arrangement of the regions made of sub mediums has such a regularity in the radial direction of the optical fiber that the light with given wavelength, propagation coefficient and electric field distribution propagates along the fiber axis and has not less than 50% of its total propagating power in the core region, and the arrangement does not have translational symmetry in cross section.

The main medium is a medium which can practicably constitute the optical fiber by itself and the main medium region must not be divided in a single optical fiber. On

the other hand, the sub medium may be a medium which cannot

constitute the optical fiber by itself. For example, the

main medium may be silica glass and the sub medium may be

gas or may be evacuated.

5   The mean refractive index n_{avg} of a given circular

annular region is defined by the following equation

$$n_{avg} = \sqrt{\frac{1}{\pi(b^2 - a^2)}\int_a^b\!\!\int n^2(r, \theta)d\theta\ rdr} \qquad (1)$$

where "a" and "b" are respectively the inner radius and the

outer radius of the circular annular region, and r and θ

10   are polar coordinates in the cross section and n (r, θ) is

a function giving the refractive index at the position (r,

θ).

        According to the present invention, by arranging the

sub mediums with a regularity in the radial direction of

15   the fiber, it becomes possible to regularly change the mean

refractive index in the radial direction in the cladding

region. Eventually, it becomes possible to confine the

light in the core by Bragg reflection. Moreover the use

of the sub medium enables grater change in the mean refractive

20   index than the conventional doped-glass technique and can

realize stronger optical confinement to the core than the

conventional technique.

        Further, since the arrangement of the sub mediums does

not have translational symmetry, the core diameter is not

25   limited to integer times of the cell size. The great freedom

7

in selecting the core diameter makes it possible to optimize the number of guided modes and the strength of the optical confinement of guided mode.

The translational symmetry of an arrangement is a property that the arrangement stays substantially unvaried when it is moved in a given direction by a given distance. Here, the vector specifying the direction and the distance of such movement operation is called a lattice vector. Further, the two-dimensional translational symmetry of an arrangement is a property that the arrangement has two independent lattice vectors.

It is preferable that the regions made of sub mediums are substantially arranged on one or more concentric circumferences centered at the fiber axis in the cross section of the fiber. Due to such a constitution, the mean refractive index of an annular region containing one of the circumferences on which the sub mediums are arranged can be made greatly different from that of the neighboring annular regions, and hence strong optical confinement can be realized.

Alternately, it is preferable that the cladding region consists of a plurality of concentric cylindrical regions, where regions having high and low mean refractive indices are arranged alternately in the radial direction.

In this manner, by alternating the high mean refractive index regions and the low mean refractive index regions,

a mode coupling is generated between cylindrical lightwaves propagating outward and inward so that it becomes possible to reflect the cylindrical lightwave propagating outward efficiently and confine it to the core region.

5   It is preferable that respective optical thicknesses of respective cylindrical regions effectively equal to the quarter wavelength of the given mode optical wave. Here, "optical thicknesses effectively equal to the quarter wavelength" means a condition where the diagonal components

10   of the characteristic matrix Mi expressed below become substantially zero.

$$Mi = \begin{bmatrix} m_{11} & m_{12} \\ m_{21} & m_{22} \end{bmatrix} = \frac{\pi \kappa_i \sqrt{a_{i-1} a_i}}{-2} \times$$

$$\begin{bmatrix} J_v(i-1)N_{v+1}(i) - J_{v+1}(i)N_v(i-1) & -\eta_i^{-1}\{J_v(i-1)N_v(i) - J_v(i)N_v(i-1)\} \\ \eta_i\{J_{v+1}(i-1)N_{v+1}(i) - J_{v+1}(i)N_{v+1}(i-1)\} & J_v(i)N_{v+1}(i-1) - J_{v+1}(i-1)N_v(i) \end{bmatrix}$$

where, a_{i-1} is the inner radius of the i-th cylindrical region, a_i is the outer radius of the i-th cylindrical region and

15   κ_i is the propagation constant in the radial direction in the i-th cylindrical region which is defined as follows.

$$\kappa_i = \sqrt{n_i^2 k_0^2 - \beta^2}$$

where, n_i is the refractive index of the i-th cylindrical region, k_0 is the wave number in vacuum, and β is the a

20   propagation constant in the axial direction. Further, η_i is the effective refractive index of the i-th cylindrical region, wherein

$\eta_i = -k_0/\kappa_i$ for TE mode

$\eta_i = k_0 n_i^2/\kappa_i$ for TM mode

$\eta_i \approx -\kappa_i/\beta$ for LP_{01} mode

Further, J_v and N_v are the first-kind and second-kind Bessel functions of the v-th order respectively. Also, J_v ($\kappa_i a_i$) is expressed as $J_v(i)$, $N_v(\kappa_i a_i)$ is expressed as $N_v(i)$, $J_v(\kappa_i a_{i-1})$ is expressed as $J_v(i-1)$ and $N_v(\kappa_i a_{i-1})$ is expressed as $N_v(i-1)$.

Although, it is in some cases difficult to make both of the diagonal components of Mi exactly equal to zero, the inventors have found out that it is sufficient for tight confinement of light to the core to make the diagonal components m_{11} and m_{22} substantially equal to zero alternately, that is, to make m_{11} substantially equal zero in the i-th region, m_{22} substantially equal to zero in the (i+1)-th region, and so forth. Such a condition to achieve high reflectivity in the cladding and tight confinement of light to the core is called a pseudo quarter wavelength condition.

By forming the core region by a void or silica glass, the transmission loss can be reduced. Further, by making the core of an optical gain medium, an optical amplifier having the gain characteristics with small dependency on wavelength can be realized. In a constitution where the core region is composed of an inner core region and an outer core region which surrounds the inner core region and has the refractive index lower than the refractive index of the inner core region, it becomes possible to reduce the bending loss in the basic mode without deteriorating the cut-off

characteristics of higher order modes.

This optical fiber can be suitably used as a band-pass optical filter and a gain equalizer. Also, an optical transmission path can be constituted by such an optical fiber and another optical fiber whose dispersion is of the opposite sign to that of such an optical fiber.

Brief Description of the Drawings

Fig. 1 is a cross-sectional view showing a basic constitution of an optical fiber according to the present invention;

Fig. 2 is a view which schematically shows the structure;

Fig. 3 and Fig. 4 are figures showing the simulation results of the first embodiment and second embodiment, respectively;

Fig. 5 is a figure showing characteristics of the chromatic dispersion D and the mode field diameter MFD to the wavelength λ in the second embodiment;

Fig. 6 is a figure showing the simulation result of the third embodiment; and

Fig. 7 is a cross-sectional view showing the structure of an optical fiber of the fourth embodiment.

Best Modes for Carrying Out the Invention

Preferred embodiments of the present invention are explained in detail hereinafter in conjunction with attached drawings. To facilitate the comprehension of the

explanation, the same reference numerals denote the same

parts, where possible, throughout the drawings, and a

repeated explanation will be omitted.

(First embodiment)

Fig. 1 is a transverse cross-sectional view showing

the basic constitution of an optical fiber 1 according to

the present invention. As shown in Fig. 1, the optical fiber

1 has a cross-sectional structure which arranges Nk pieces

of voids 2 equidistantly on circumferences having radii Rk

(k = 0... M) centered on a fiber axis. The voids arranged

on a circumference of a radius of Rk have substantially the

same diameter dk. Figure 1 shows a part of the

cross-sectional structure corresponding to k = 0, ..., 5. In

the optical fiber 1 shown in Fig. 1, the number M of the

voids 2 in the radial direction is set to M = 9 and Rk, dk,

Nk respectively take values shown in Table 1.

Table 1 : Arrangement of voids 2 in the optical fiber of
the first embodiment.

k	0	1	2	3	4	5	6	7	8	9
Rk [μm]	0	3.59	4.35	5.12	5.88	6.64	7.39	8.15	8.91	9.67
dk [μm]	6.05	0.340	0.335	0.332	0.329	0.327	0.326	0.325	0.324	0.323
Nk	1	24	30	36	42	48	54	60	66	72

A void (cavity) having a diameter of 6.05 μm which

is positioned at the center of the optical fiber 1 corresponds

to the core 3 and a region around the core 3 constitutes

12

a cladding region 5 formed of silica glass 4 and the voids
2. The cladding region 5 consists of circular annular
regions having a high mean refractive index and a low mean
refractive index alternately stacked in the radial direction.
The refractive indices of the silica glass 4 and the voids
2 are respectively 1.444 and 1 at a wavelength of 1550 nm.

With a plurality of voids 2 which are arranged on the
concentric circumferences centered on the fiber axis, the
cladding region 5 has a structure in which the circular
annular regions having the high mean refractive index and
the circular annular regions having the low mean refractive
index are alternately laminated in the radial direction.
Fig. 2 shows this mode in a schematic manner. Here, the
circular annular regions $5k$ ($k=1, ..., 2M$) are numbered from
the inner side to the outer side. The circular annular
regions with odd number 5_1, 5_3, 5_5, $5_{2M-1(=17)}$ do not include
voids 2 and consists only of silica glass 4. Accordingly,
the refractive indices of these circular annular regions
are all equal to 1.444 at the wavelength of 1550 nm.

On the other hand, in the circular annular regions
with even number 5_2, 5_4, 5_6, $5_{2M(=18)}$, which are disposed between
the circular annular regions with odd number 5_1, 5_3, 5_5,
$5_{2M-1(=17)}$, the voids 2 are disposed at an interval along
circumferences each of which is centered at the fiber axis
and has a radius equal to the mean of the inner and outer
radii of the circular annular region. The thicknesses of

the circular annular regions are all 0.40 μm. The mean refractive indices of these regions are all 1.350 at a wavelength of 1550 nm, according to equation (1). Accordingly, the even-numbered circular annular regions

5 have the lower mean refractive indices than the odd-numbered circular annular regions.

The propagation constant κ in the radial direction, the phase thickness δ and the diagonal components m_{11}, m_{22} of the characteristic matrix at a wavelength of 1550 nm of

10 the core region 1 and respective circular annular regions 5_1 to 5_{18} are shown in Table 2. Denoting the physical thickness of the layer as t, the phase thickness is defined by $\delta = \kappa t$.

Table 2 : Structural parameters of respective regions of the optical fiber of the embodiment 1

	κ	δ	m_{11}	m_{22}
Core region 1	1.26	3.81		
Circular annular region 5_1	4.41	1.61	3×10^{-3}	-4×10^{-5}
Circular annular region 5_2	3.89	1.55	8×10^{-4}	-2×10^{-3}
Circular annular region 5_3	4.41	1.60	2×10^{-3}	-2×10^{-5}
Circular annular region 5_4	3.89	1.55	4×10^{-4}	-2×10^{-3}
Circular annular region 5_5	4.41	1.59	1×10^{-3}	-5×10^{-5}
Circular annular region 5_6	3.88	1.55	3×10^{-4}	-1×10^{-3}
Circular annular region 5_7	4.41	1.59	1×10^{-3}	-1×10^{-4}
Circular annular region 5_8	3.89	1.55	1×10^{-4}	-1×10^{-3}
Circular annular region 5_9	4.41	1.58	7×10^{-4}	-2×10^{-4}
Circular annular region 5_{10}	3.89	1.56	1×10^{-4}	-8×10^{-4}
Circular annular region 5_{11}	4.41	1.58	5×10^{-4}	-2×10^{-4}
Circular annular region 5_{12}	3.89	1.56	7×10^{-5}	-7×10^{-4}
Circular annular region 5_{13}	4.41	1.58	4×10^{-4}	-2×10^{-4}
Circular annular region 5_{14}	3.88	1.55	-2×10^{-5}	-7×10^{-4}
Circular annular region 5_{15}	4.41	1.58	3×10^{-4}	-1×10^{-4}
Circular annular region 5_{16}	3.89	1.56	-9×10^{-6}	-5×10^{-4}
Circular annular region 5_{17}	4.41	1.58	3×10^{-4}	-9×10^{-5}
Circular annular region 5_{18}	3.88	1.55	-5×10^{-5}	-5×10^{-4}

As shown in Table. 2, the phase thicknesses δ of respective layers substantially correspond to π /2, and the diagonal components of the characteristic matrix m_{11} and m_{22} become substantially zero in the even-numbered and odd-numbered circular annular regions, respectively, so that the pseudo quarter wavelength condition is satisfied. As a result, the cladding region 5 efficiently reflects cylindrical lightwave propagating outward and confines the lightwave to the core region 1. The present invention realizes higher reflectivity in the cladding than the

conventional technique based on Ge-doped silica because the mean refractive index difference between the even-numbered circular annular regions with a plurality of voids and the odd-numbered circular annular regions without voids is as high as 6.7 %, which could not be realized by the conventional technique.

The optical fiber according to this embodiment can be fabricated by a fiber drawing step in which one end of a fiber preform is heated and drawn to form the optical fiber. As a result, compared with the conventional technique in which fiber is made by deposition, optical fiber can be fabricated to a long length and with a good uniformity along the length. For example, by drawing a preform with a diameter of 20 mm and a length of 300 mm, optical fiber with a diameter of 125 μm can be fabricated to a length of 7.6 km.

The core diameter, which is set to 6.05 μm in this embodiment, is not limited by the regularity on the cladding structure. This is the difference from the conventional full PBG guided-type optical fiber in which the core diameter is restricted to integer times of the cell diameter. The optical fiber of this embodiment can provide a wide selection range of core diameter. As a result, it becomes possible to control the strength of confinement of light and the number of modes.

Further, by alternating the circular annular regions having high and low mean refractive indices in the radial

16

direction, efficient mode coupling is realized between cylindrical lightwaves propagating outward and inward, whereby it becomes possible to reflect the cylindrical lightwave propagating outward and confine the lightwave to

5   the core.

Fig. 3 shows the simulation result with respect to the optical power distribution in the radial direction together with the distribution of the mean reflective index n_{avg} in the optical fiber 1. The optical fiber 1 has the

10   guided mode at a wavelength of 1550 nm and the mode reflective index n_{eq} of the guided mode is 0.9507. Further, the electric field distribution of the guided mode is similar to the TE mode electric field distribution in a step-index type optical fiber. That is, an electric field vector is aligned along

15   the circumferential direction with respect to the fiber axis.

In Fig. 3, the distribution of optical power P in the radial direction in the cross section is shown with respect to two directions consisting of an arbitrary X direction and a Y direction which is perpendicular to the X direction.

20   The position in the radial direction is denoted as r. It is understood that the optical power is confined in the core due to the regular structure of the mean refractive index. Here, not less than 90 % of the total propagation power propagates through the core. Since the core 3 consists of

25   a void in this optical fiber, the optical fiber exhibits such characteristics as low transmission loss, low

17

have voids 2 along a circumference which is centered at the

fiber axis and has a radius equal to the mean of the inner

and outer radii of the circular annular region, and have

the low refractive index (1.350 at a wavelength of 1550 nm)

5   are alternately arranged.

The propagation coefficients κ, the phase thicknesses

δ, the diagonal components m_{11}, m_{22} of characteristic matrix

of the core region 1 and respective circular annular regions

5_1 to 5_{16} at a wavelength of 1550 nm are shown in Table 4.

10

Table 4: Structural parameters of respective regions of the

optical fiber of the second embodiment.

	κ	δ	m_{11}	m_{22}
Core region 1	0.52	2.18		
Circular annular region 5_1	4.25	1.54	-7×10^{-5}	-2×10^{-3}
Circular annular region 5_2	3.71	1.60	2×10^{-3}	-2×10^{-4}
Circular annular region 5_3	4.25	1.55	-1×10^{-5}	-1×10^{-3}
Circular annular region 5_4	3.71	1.59	1×10^{-3}	-2×10^{-4}
Circular annular region 5_5	4.25	1.55	-1×10^{-5}	-1×10^{-3}
Circular annular region 5_6	3.71	1.59	1×10^{-3}	-1×10^{-4}
Circular annular region 5_7	4.25	1.55	-7×10^{-5}	-8×10^{-4}
Circular annular region 5_8	3.71	1.59	9×10^{-4}	-3×10^{-5}
Circular annular region 5_9	4.25	1.55	-4×10^{-5}	-7×10^{-4}
Circular annular region 5_{10}	3.71	1.58	6×10^{-4}	-1×10^{-4}
Circular annular region 5_{11}	4.25	1.56	-4×10^{-6}	-5×10^{-4}
Circular annular region 5_{12}	3.71	1.58	5×10^{-4}	-9×10^{-5}
Circular annular region 5_{13}	4.25	1.56	-3×10^{-5}	-4×10^{-4}
Circular annular region 5_{14}	3.71	1.58	4×10^{-4}	-7×10^{-5}
Circular annular region 5_{15}	4.25	1.56	-2×10^{-5}	-4×10^{-4}
Circular annular region 5_{16}	3.71	1.58	3×10^{-4}	-1×10^{-4}

As shown in Table 4, the phase thickness δ of each

20

layer corresponds to approximately $\pi/2$, and, the diagonal components of characteristic matrix m_{11} and m_{22} becomes substantially zero in the odd-numbered and even-numbered circular annular regions, respectively, and hence the pseudo quarter wavelength condition is satisfied. Accordingly, the cladding region 5 can reflect cylindrical wave propagating outward and confine the lightwave to the core region 1 tightly.

Fig. 4 shows the simulation result of the optical power distribution of the optical fiber 1 in the radial direction in the second embodiment together with the distribution of the mean refractive index n_{avg}. This optical fiber has a guided mode at a wavelength 1550 nm and the mode refractive index n_{eq} of the guided mode is 0.9899. Further, the electric field distribution of the guided mode is similar to an LP01 mode electric field distribution of a step index type optical fiber. That is, the direction of the electric field is substantially uniform in the cross section. By taking this direction as a Y axis and a direction perpendicular to this direction in the cross section as an X axis, the distributions of optical power P along respective axes become as shown in Fig. 4. It is understood that the optical power is confined in the core due to the regular structure of the mean refractive indices. Here, not less than 90% of the total propagation power propagates through the core region.

In the optical fiber of this second embodiment also,

since the core 3 consists of a void, the optical fiber has characteristics such as low optical loss, low non-linearity and low material dispersion. Further, since the cladding region 5 consists of the silica glass 4 and the voids 2, the optical loss is low and the reflectivity in the cladding region 5 is high. Further, since the main medium is silica glass and the sub medium is air, an optical fiber based on guiding by Bragg reflection can be easily fabricated to a long length and with a good uniformity by fiber drawing compared with conventional technique.

Fig. 5 shows characteristics of the chromatic dispersion D and the mode field diameter MFD to wavelength λ of the optical fiber of this embodiment. The mode field diameter MFD takes the smallest value in the vicinity of the wavelength of 1600 nm, which means that the reflection wavelength band of the cladding region 5 is present around 1600 nm. Further, the mode field diameter MFD increases as the wavelength deviates from 1600 nm, which means that the pseudo quarter wavelength condition becomes less satisfied and optical confinement becomes weak as the wavelength deviates from the reflection wavelength band.

As optical confinement becomes weak, the optical loss due to the leakage of light to the outside of the fiber increases. Accordingly, with the deviation of the optical wavelength from the reflection wavelength band, the optical loss increases. As a result, it becomes possible to realize

an optical filter which adopts the reflection wavelength band as transmission band and a gain equalizer using the wavelength dependency of the optical loss.

Further, as the optical wavelength deviates from the reflection wavelength band, the mode group refractive index increases, which results in increase in the absolute value of the chromatic dispersion. The chromatic dispersion and the chromatic dispersion slope become negative in the shorter wavelength side of the reflection wavelength band and positive in the longer wavelength side of the reflection wavelength band. Such characteristics of the optical fiber are suitable for the compensation of the chromatic dispersion and the chromatic dispersion slope of an optical transmission path.

(Third embodiment)

An optical fiber of the third embodiment according to the present invention has a basic structure which is identical with those of the optical fibers of the first and second embodiments. However, in the third embodiment, the number M of voids 2 in the radial direction is 9 and Rk, dk and Nk take values different from those of the first and second embodiments as shown in Table 5.

Table 5: Arrangement of voids 2 in an optical fiber of the third embodiment.

K	0	1	2	3	4	5	6	7	8	9
Rk [μm]	0	5.38	7.84	10.29	12.73	15.17	17.61	20.04	22.47	24.90
dk [μm]	7.36	0.434	0.465	0.484	0.497	0.506	0.513	0.519	0.524	0.527
Nk	1	24	30	36	42	48	54	60	66	72

In contrast to the first and second embodiments, a
circular region positioned at the center of the fiber is
formed of pure silica glass and constitutes a core 3. The
diameter of this circular region is 7.36 μm. A cladding
region 5 surrounding the core 3 is composed of silica glass
4 doped with 30 mol % of Ge and voids 2. Refractive indices
of the core 3, the Ge-doped silica glass 4 and the voids
2 at a wavelength of 1550 nm are respectively 1.444, 1.488
and 1.

In this embodiment also, circular annular regions 5_1,
5_3, 5_5, …, 5_{17} which consist only of Ge-doped silica glass
4 and has a high refractive index (1.488 at a wavelength
of 1550 nm) and circular annular regions 5_2, 5_4, 5_6, …, 5_{18}
having voids 2 along a circumference which is centered at
the fiber axis and has a radius equal to the mean of the
inner and outer radii of the circular annular region, and
has a low refractive index (1.460 at a wavelength of 1550
nm) are alternately arranged.

The propagation coefficients κ in the radial direction,
the phase thickness δ, the diagonal components m_{11}, m_{22} of

24

the characteristic matrix of the core region 1 and respective circular annular regions 5_1 to 5_{18} at a wavelength of 1550 nm are shown in Table 6.

Table 6: Structural parameters of respective regions of the optical fiber of the third embodiment.

	κ	δ	m_{11}	m_{22}
Core region 1	0.62	2.29		
Circular annular region 5_1	1.59	1.49	-1×10^{-3}	-2×10^{-3}
Circular annular region 5_2	1.07	1.63	2×10^{-2}	-4×10^{-3}
Circular annular region 5_3	1.59	1.51	-6×10^{-4}	-6×10^{-3}
Circular annular region 5_4	1.07	1.60	7×10^{-3}	-2×10^{-3}
Circular annular region 5_5	1.59	1.53	-5×10^{-4}	-4×10^{-3}
Circular annular region 5_6	1.07	1.59	4×10^{-3}	-2×10^{-3}
Circular annular region 5_7	1.59	1.53	-4×10^{-4}	-2×10^{-3}
Circular annular region 5_8	1.07	1.58	2×10^{-3}	-1×10^{-3}
Circular annular region 5_9	1.59	1.54	-3×10^{-4}	-2×10^{-3}
Circular annular region 5_{10}	1.07	1.57	1×10^{-3}	-1×10^{-3}
Circular annular region 5_{11}	1.59	1.54	-3×10^{-4}	-1×10^{-3}
Circular annular region 5_{12}	1.07	1.57	9×10^{-4}	-9×10^{-4}
Circular annular region 5_{13}	1.59	1.54	-2×10^{-4}	-9×10^{-4}
Circular annular region 5_{14}	1.07	1.56	4×10^{-4}	-9×10^{-4}
Circular annular region 5_{15}	1.59	1.55	-2×10^{-4}	-7×10^{-4}
Circular annular region 5_{16}	1.07	1.56	3×10^{-4}	-8×10^{-4}
Circular annular region 5_{17}	1.59	1.55	-2×10^{-4}	-6×10^{-4}
Circular annular region 5_{18}	1.07	1.56	2×10^{-4}	-7×10^{-4}

As shown in Table 6, the phase thickness δ of each layer corresponds to approximately $\pi/2$, and the diagonal components of the characteristic matrix m_{11} and m_{22} become substantially zero in the odd-numbered and even-numbered circular annular regions, respectively, and hence the pseudo quarter wavelength condition is satisfied. Accordingly,

the cladding region 5 can efficiently reflect cylindrical lightwave propagating outward and confine the lightwave to the core tightly.

Fig. 6 shows the simulation result of distribution of the optical power P in the radial direction in the optical fiber 1 of the third embodiment together with the distribution of the mean refractive index n_{avg}. This optical fiber has a guided mode at a wavelength 1550 nm and the mode refractive index n_{eq} of the guided mode is 1.4359. Further, the electric field distribution of the guided mode is similar to an LP01 mode electric field distribution of a step index type optical fiber. That is, the direction of the electric field is substantially uniform in the cross section. By taking this direction as Y axis and the direction perpendicular to this direction in the cross section as X axis, optical power distributions along respective axes are shown in Fig. 6. It is understood that the optical power is confined in the core due to the regular structure of the mean refractive indices. Here, not less than 90% of the total propagation power propagates through the core region.

In the optical fiber of this third embodiment also, since the core 3 is silica glass, low optical loss can be realized. Further, since the cladding region 5 consists of silica based glass 4 and voids 2, the optical loss is low and the reflectivity of the cladding region 5 is high. Further, since the main medium is silica based glass and

the sub medium is air, an optical fiber based on guiding

by Bragg reflection can be fabricated to a long length and

a good uniformity along the length by fiber drawing compared

with the conventional technique which makes fiber by

5   deposition.

Further, in this optical fiber, by doping an element

such as Er into at least a part of the core, the core can

be formed into an optical gain medium. Usually, the gain

in the optical gain medium has a wavelength dependency. In

10   the optical fiber of this third embodiment, the optical loss

depends on the wavelength as in the case of the optical fiber

of the second embodiment. Accordingly, by designing the

wavelength dependency of the optical loss so that it cancels

the wavelength dependency of the gain characteristics, the

15   gain characteristics with small wavelength dependency can

be realized. As a result, an optical amplifier having the

gain characteristics with small wavelength dependency which

is suitable for an optical communication of a long distance

and a large capacity can be realized.

20   Further as shown in Fig. 7, a core region 3 may consist

of an inner core 31 and an outer core 32 which surrounds

the inner core 31 and has the refractive index lower than

that of the inner core 31 (hereinafter called "Fourth

embodiment"). In the conventional optical fiber based on

25   total internal reflection, optical properties such as

chromatic dispersion and effective core area are restricted

27

by bending loss. In the present embodiment, light is confined to the inner core region 31 due to total internal reflection between the inner core 31 and the outer core 32. Further, the regularity in the radial profile of the mean refractive index in the cladding 5 prevents light from leaking to the outside of the fiber, so that the bending loss can be reduced compared with an optical fiber which consists of only the core region 3 (an optical fiber in which the outer core 32 corresponds to a cladding region). As a result, the range of optical fiber characteristics which can be realized is broadened. Further, although reduction in bending loss of the fundamental mode often accompanies degradation in the cut-off characteristics of higher modes, according to the optical fiber of this embodiment, since the reflectivity of the cladding region has mode-selective characteristics, by designing the cladding structure so that the light of the fundamental mode is selectively reflected, the bending loss of the fundamental mode can be reduced without degrading the cut-off characteristics of higher order modes.

Further, in the optical fiber of the present invention, when the light has a wavelength at which the pseudo quarter wavelength condition is not satisfied is not reflected by the cladding region, so that the light leaks through the cladding region to the outside and hence is not guided along the fiber length. Accordingly, the optical fiber of this

28

invention can be used as an optical filter which transmits only the light having the wavelength at which the pseudo quarter wavelength condition is satisfied, that is, the light in the reflection wavelength band.

The above mentioned pseudo quarter wavelength condition is a condition under which the cladding region most efficiently reflects lightwave, and there exists a wavelength where the condition is satisfied best and the reflectivity is maximized. As the wavelength of the light deviates from such a wavelength, the reflectivity of the cladding decreases, and the leakage loss increases. Such a characteristics can be used for realizing a wavelength-dependent transmission loss. In a wavelength division multiplexing optical communication, the wavelength dependent transmission loss can be used as a gain equalizer which minimizes the difference in the optical powers between wavelength channels. Accordingly, an optical communication of a large capacity and a long distance can be realized.

Further, in the optical fiber of the present invention, in the vicinity of the edges of the reflection wavelength band, large chromatic dispersion can be realized and the sign of the chromatic dispersion is different between two edges of the reflection wavelength band, and hence the positive or negative chromatic dispersion can be realized in a given wavelength band. Accordingly, by constituting

an optical transmission path comprising of this optical fiber and an optical fiber which has chromatic dispersion of the opposite sign, it becomes possible to compensate for the dispersion of the optical transmission path. Accordingly, an optical transmission path having a small total chromatic dispersion and a large transmission capacity can be realized.

As has been described heretofore, according to the present invention, large mean refractive index difference can be obtained and, at the same time, high reflectivity in the cladding can be realized. Although the optical fiber of the present invention is similar to the conventional full PBG optical fiber in that the optical fiber has the voids and uses Bragg reflection, the optical fiber of the present invention remarkably differs from the conventional full PBG optical fiber in that the arrangement of voids does not have the translational symmetry. Since the optical fiber of the present invention does not have translational symmetry, the range of the realizable value of the core diameter is broadened. As a result, the number of the guided modes and the degree of optical confinement of the guided mode can be controlled in a wide range. Further, by choosing silica glass as the main medium and a gas or vacuum state as the sub medium, it becomes possible to fabricate optical fiber to a long length and with a good uniformity compared with the conventional technique.

WO 01/88578

Industrial Applicability

The optical fiber according to the present invention is suitable for an optical transmission path, a dispersion compensator, an optical filter, an optical power equalizer, 5 an optical amplifier or the like.

CLAIMS

1. An optical fiber consisting of a core region and a cladding region which surrounds said core region and has a plurality of regions spaced apart in cross section and made of sub mediums, whose refractive indices differ from that of a main medium constituting said cladding region, wherein said core region has lower mean refractive index than that of said cladding region, and wherein:

the arrangement of said regions made of sub mediums has such a regularity in the radial direction of said optical fiber that the light with given wavelength, propagation coefficient and electric field distribution propagates along the fiber axis and has not less than 50% of its total propagating power in said core region, and said arrangement does not have translational symmetry in cross section.

2. An optical fiber according to claim 1, wherein said regions made of sub mediums are substantially arranged on one or more concentric circumferences centered at the fiber axis in the cross section of the fiber.

3. An optical fiber according to claim 1, wherein said cladding region consists of a plurality of concentric cylindrical regions, where regions having high and low mean refractive indices are arranged alternately in the radial direction.

4. An optical fiber according to claim 3, wherein the optical thicknesses of said respective cylindrical

regions effectively equal to the quarter wavelength of the given mode optical wave.

5.   An optical fiber according to claim 1, wherein said main medium is silica glass and said sub medium is gas or vacuum.

6.   An optical fiber according to claim 1, wherein said core region is a void.

7.   An optical fiber according to claim 1, wherein said core region is made of silica glass.

8.   An optical fiber according to claim 1, wherein said core region is made of optical gain medium.

9.   An optical fiber according to claim 1, wherein said core region is composed of an inner core region and an outer core region surrounding said inner core region and having a lower refractive index than that of said inner core region.

10.   A band-pass optical filter composed of said optical fiber according to claim 1.

11.   A gain equalizer composed of said optical fiber according to claim 1.

12.   An optical transmission path including said optical fiber according to claim 1 and an optical fiber whose dispersion is of the opposite sign to this optical fiber.

Fig.1

Fig.2

Fig.3

Fig.4

Fig.5

Fig.6

Fig.7

(51) International Patent Classification⁷: G02B 6/16. 6/22

(21) International Application Number: PCT/JP01/03805

(22) International Filing Date: 2 May 2001 (02.05.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2000-142119   15 May 2000 (15.05.2000)   JP

(71) Applicant: SUMITOMO ELECTRIC INDUSTRIES, LTD. [JP/JP]; 5-33. Kitahama 4-chome, Chuo-ku, Osaka-shi, Osaka 541-0041 (JP).

(72) Inventors: HASEGAWA, Takemi: c/o Yokohama Works of Sumitomo Electric Industries. Ltd.. 1. Taya-cho, Sakae-ku. Yokohama-shi, Kanagawa 244-8588 (JP). SASAOKA, Eisuke: c/o Yokohama Works of Sumitomo Electric Industries, Ltd.. 1. Taya-cho, Sakae-ku, Yokohama-shi, Kanagawa 244-8588 (JP). NISHIMURA,

Masayuki; c/o Yokohama Works of Sumitomo Electric Industries, Ltd., 1, Taya-cho, Sakae-ku. Yokohama-shi, Kanagawa 244-8588 (JP).

(74) Agents: HASEGAWA, Yoshiki et al.; SOEI PATENT AND LAW FIRM, Okura-honkan, 6-12. Ginza 2-chome, Chuo-ku, Tokyo 104-0061 (JP).

(81) Designated States (national): AU, CA, CN, KR.

(84) Designated States (regional): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).

Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:
25 April 2002

(54) Title: OPTICAL FIBER

(57) Abstract: In an optical fiber 1 having a core region 3 and a cladding region 5 which surrounds the core region 3, wherein a plurality of regions made of sub mediums 2 having refractive index different from that of the main medium 4 constituting the cladding region 5 are spaced apart in cross section of the cladding region 5 and the mean refractive index of the core region 3 is lower than that of the cladding region 5, the sub-medium regions 2 are regularly arranged in the radial direction of the optical fiber 1 such that the light having given wavelength, propagation coefficient and electric field distribution propagates along the fiber axis and has not less than 50 % of a total propagating power in the core region 3, and this arrangement does not have translational symmetry in cross section.

WO 01/88578 A3

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7   G02B6/16   G02B6/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7   G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No
E	WO 01 63328 A (SUMITOMO ELECTRIC INDUSTRIES) 30 August 2001 (2001-08-30) figures 1,7,12-15 page 9; tables 1,2 ---	1-3,11
A	EP 0 621 496 A (ASAHI CHEMICAL IND) 26 October 1994 (1994-10-26) claims; figures 1,2 column 2, line 37 - line 57 column 3, line 1 - line 40 ---	1,2,6
A	US 4 139 262 A (MAHLEIN HANS ET AL) 13 February 1979 (1979-02-13) column 2, line 62 - line 68 column 3, line 1 - line 38 claim 3; figure ---	1,3,4,10

-/--

[X] Further documents are listed in the continuation of box C.   [X] Patent family members are listed in annex.

° Special categories of cited documents :

'A' document defining the general state of the art which is not considered to be of particular relevance
'E' earlier document but published on or after the international filing date
'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
'O' document referring to an oral disclosure, use, exhibition or other means
'P' document published prior to the international filing date but later than the priority date claimed

'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
'&' document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
12 February 2002	05/03/2002

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl. Fax: (+31-70) 340-3016	Mathyssek, K

Form PCT/ISA/210 (second sheet) (July 1992)

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category°	Citation of document. with indication,where appropriate. of the relevant passages	Relevant to claim No
A	US 5 742 722 A (IMOTO KATSUYUKI) 21 April 1998 (1998-04-21) figures 8,11,13,14,18,20-22 claims ---	1,8
A	US 5 802 236 A (DIGIOVANNI DAVID JOHN ET AL) 1 September 1998 (1998-09-01) claims; figures column 4, line 55 - line 67 column 5 -column 8 ---	1-3,5,7, 11
A	BROENG J ET AL: "PHOTONIC CRYSTAL FIBERS: A NEW CLASS OF OPTICAL WAVEGUIDES" OPTICAL FIBER TECHNOLOGY, ACADEMIC PRESS, LONDON, US, vol. 5, no. 3, July 1999 (1999-07), pages 305-330, XP001023773 ISSN: 1068-5200 figure 16 page 323 -page 324 ---	1,6,7
A	US 5 448 674 A (VENGSARKAR ASHISH M ET AL) 5 September 1995 (1995-09-05) figure 3 column 6, line 22 - line 34 ---	1,12
A	J.MARCOU ET. AL.: "Monomode photonic band gap fibers for dispersion shifting towards short wavelengths" 25TH EUROPEAN CONFERENCE ON OPTICAL COMMUNICATION, vol. 1, 27 - 28 September 1999, pages 24-25, XP002189996 cited in the application the whole document -----	1,3

		Application No
		PCT/JP 01/03805

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
WO 0163328	A	30-08-2001	AU	3415301 A	03-09-2001
			WO	0163328 A1	30-08-2001
			US	2001028775 A1	11-10-2001
			WO	0184198 A1	08-11-2001
			WO	0179902 A1	25-10-2001
			US	2001038740 A1	08-11-2001
EP 0621496	A	26-10-1994	WO	9408261 A1	14-04-1994
			DE	69225242 D1	28-05-1998
			DE	69225242 T2	24-12-1998
			EP	0621496 A1	26-10-1994
			GB	2302183 A ,B	08-01-1997
			KR	136752 B1	15-06-1998
			US	5471553 A	28-11-1995
US 4139262	A	13-02-1979	DE	2442859 A1	18-03-1976
US 5742722	A	21-04-1998	JP	3006474 B2	07-02-2000
			JP	9230156 A	05-09-1997
			JP	3006476 B2	07-02-2000
			JP	9265021 A	07-10-1997
			FR	2745392 A1	29-08-1997
			GB	2310506 A ,B	27-08-1997
			US	5703987 A	30-12-1997
US 5802236	A	01-09-1998	DE	69707201 D1	15-11-2001
			EP	0810453 A1	03-12-1997
			JP	10095628 A	14-04-1998
US 5448674	A	05-09-1995	EP	0668520 A2	23-08-1995
			JP	7270636 A	20-10-1995
			DE	69324886 D1	17-06-1999
			DE	69324886 T2	30-09-1999
			EP	0598554 A1	25-05-1994
			JP	6222235 A	12-08-1994

THIS PAGE BLANK (USPTO)